

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
11.750	42.00	H-40	1040	1980	1980		1980	307		554	478	0.333	11.084	10.928	11.000
11.750	47.00	J-55	1510	3070		3070	3070	477		807	737	0.375	11.000	10.844	
11.750	47.00	K-55	1510	3070		3070	3070	509		935	737	0.375	11.000	10.844	
11.750	47.00	HCK-55	2000	3070		3070	3070	638		1054	737	0.375	11.000	10.844	
11.750	54.00	J-55	2070	3560		3560	3560	568		931	850	0.435	10.880	10.724	
11.750	54.00	K-55	2070	3560		3560	3560	606		1079	850	0.435	10.880	10.724	
11.750	54.00	HCK-55	3100	3560		3560	3560	760		1216	850	0.435	10.880	10.724	
11.750	60.00	J-55	2660	4010	4010		4010	649		1042	952	0.489	10.772	10.616	10.625
11.750	60.00	K-55	2660	4010	4010		4010	693		1208	952	0.489	10.772	10.616	10.625
11.750	60.00	HCK-55	4360	4010	4010		4010	869		1361	952	0.489	10.772	10.616	10.625
11.750	60.00	L-80	3180	5830	5830		5830	913		1399	1384	0.489	10.772	10.616	10.625
11.750	60.00	HCL-80	4410	5830	5830		5830	1055		1555	1384	0.489	10.772	10.616	10.625
11.750	60.00	N-80	3180	5830	5830		5830	924		1440	1384	0.489	10.772	10.616	10.625
11.750	60.00	HCN-80	4410	5830	5830		5830	1055		1555	1384	0.489	10.772	10.616	10.625
11.750	60.00	C-90	3360	6550	6550		6550	1011		1517	1557	0.489	10.772	10.616	10.625
11.750	60.00	H2S-90	4410	6550	6550		6550	1055		1555	1557	0.489	10.772	10.616	10.625
11.750	60.00	S-95	4410	6920	6920		6920	1077		1638	1644	0.489	10.772	10.616	10.625
11.750	60.00	T-95	3440	6920	6920		6920	1066		1596	1644	0.489	10.772	10.616	10.625
11.750	60.00	H2S-95	4410	6920	6920		6920	1066		1596	1644	0.489	10.772	10.616	10.625
11.750	60.00	C-95	3440	6920	6920		6920	1066		1596	1644	0.489	10.772	10.616	10.625
11.750	60.00	HCP-110	4410	8010	8010		8010	1242		1877	1903	0.489	10.772	10.616	10.625
11.750	60.00	P-110	3610	8010	8010		8010	1242		1877	1903	0.489	10.772	10.616	10.625
11.750	60.00	HCQ-125	4410	9100	9100		9100	1396		2074	2163	0.489	10.772	10.616	10.625
11.750	60.00	Q-125	3680	9100	9100		9100	1396		2074	2163	0.489	10.772	10.616	10.625
11.750	65.00	L-80	3870	6360	6360		6360	1007		1521	1505	0.534	10.682	10.526	10.625
11.750	65.00	HCL-80	5740	6360	6360		6360	1152		1691	1505	0.534	10.682	10.526	10.625
11.750	65.00	N-80	3870	6360	6360		6360	1019		1566	1505	0.534	10.682	10.526	10.625
11.750	65.00	HCN-80	5740	6360	6360		6360	1164		1691	1505	0.534	10.682	10.526	10.625
11.750	65.00	H2S-90	5140	7160	7160		7160	1164		1691	1639	0.534	10.682	10.526	10.625
11.750	65.00	S-95	5740	7560	7560		7560	1189		1781	1788	0.534	10.682	10.526	10.625
11.750	65.00	H2S-95	5740	7560	7560		7560	1177		1736	1788	0.534	10.682	10.526	10.625
11.750	65.00	HCP-110	5740	8750	8750		8750	1371		2041	2070	0.534	10.682	10.526	10.625
11.750	65.00	P-110	4480	8750	8750		8750	1371		2041	2070	0.534	10.682	10.526	10.625
11.750	65.00	HCQ-125	5740	9940	9940		9940	1540		2256	2352	0.534	10.682	10.526	10.625
11.750	65.00	Q-125	4690	9940	9940		9940	1540		2256	2352	0.534	10.682	10.526	10.625
11.750	71.00	H2S-90	7280	7800	7800		7800	1226		1790	1838	0.582	10.586	10.430	
11.750	71.00	S-95	7280	8230	8230		8230	1306		1933	1940	0.582	10.586	10.430	
11.750	71.00	H2S-95	7280	8230	8230		8230	1293		1884	1940	0.582	10.586	10.430	
11.750	71.00	HCP-110	7280	9530	9530		9530	1506		2215	2246	0.582	10.586	10.430	
11.750	71.00	P-110	5470	9530	9530		9530	1506		2215	2246	0.582	10.586	10.430	

O.D. (INCH)	NOMINAL WEIGHT (T&C LBS/FT)	GRADE	COLLAPSE (PSI)	INTERNAL YEILD PRESSURE AT MINIMUM YIELD (PSI)				JOINT STRENGTH 1000 LBS			BODY YIELD 1000 LBS	WALL (IN)	LD (INCH)	DRIFT DIAMETER (INCH)	
				PE	STC	LTC	BTC	STC	LTC	BTC				API	SD
11.750	71.00	HCQ-125	7280	10840	10840		10840	1693		2448	2552	0.582	10.586	10.430	
11.750	71.00	Q-125	5760	10840	10840		10840	1693		2448	2552	0.582	10.586	10.430	